

Grade ATR™ Isomolded Graphite

Since 1886, UCAR Carbon Company has been supplying quality carbon and graphite products, skilled technical service, and experienced application assistance worldwide.

Advanced Graphite Materials

Grade ATR™ Isomolded Graphite

Isostatically molded UCAR® Grade ATR is a lower density version of UCAR Grade ATJ™. It is a fine grain, high strength material which can be machined to precise tolerances and a fine surface finish.

Typical Applications

- Rocket motor nozzles
- Hot pressing molds
- Mold cores
- Plungers & rams

Sizes

Grade ATR Isomolded: 16 x 16 x 65 rectangles
 12 x 25 x 80 rectangles
 8" – 24" diameter x 72" long rounds

Typical Properties at Room Temperature

	ENGLISH		METRIC	
Density	lbs/ft ³	105	g/cm ³	1.68
Average Particle Size	inches	0.001	mm	0.025
Specific Resistance	10 ⁻⁴ Ω in.	4.92	μΩm	12.5
Flexural Strength	psi	3700	kg/cm ²	260
Young's Modulus	10 ⁻⁶ psi	1.16	kg/mm ²	820
Tensile Strength	psi	3000	kg/cm ²	210
Compressive Strength	psi	8000	kg/cm ²	560
Permeability	Darcy	0.015	Darcy	0.015
Hardness	Rockwell "L"	45	Rockwell "L"	45
C.T.E. (to 100 °C)	10 ⁻⁶ /°F	1.4	10 ⁻⁶ /°C	2.5
Thermal Conductivity	BTU-ft/hr ft ² °F	58	W/mK	100
Ash Content	%	0.09	%	0.09

This information is not to be taken as a warranty of representation for which we will assume legal responsibility nor permission or recommendation to practice any patented invention without license. It is offered solely for your consideration, investigation and verification. UCAR is a registered trademark licensed for use to GrafTech International Ltd. Grade ATR and ATJ are trademarks of UCAR Carbon Company.

P.O. Box 2230, Clarksburg, WV 26302-2330
 Phone 1-800-842-8805; Fax 1-304-624-1269
 Rev. 6.03



www.graftech.com
www.ucar.com

Copyright 2003 GrafTech International Ltd.