

# Secondary Synthetic Graphite Powder GS200-850-M

Technical Data Sheet 5062

## Product Overview

Good lubrication properties, SiC free

## Applications

- Conductive polymers
- Friction materials
- Lubricants

## Typical Properties at Room Temperature\*

Characteristic	Unit	Value
<b>Purity</b>		
Ash	%	0.50
Moisture	%	0.02
Sulfur	%	0.02
<b>Sizing</b>		
10 mesh	1700 µm	0% Retained On
20 mesh	850 µm	4% Retained On
35 mesh	425 µm	91% Retained On
65 mesh	212 µm	4% Retained On
-	Pan	1% Retained On

## Guaranteed Values

Ash	% max	1.0
Moisture	% max	0.50
<b>Sizing</b>		
100%		< 10 mesh (1700 µm)
98%		> 65 mesh (212 µm)

**Notes:**

\* Properties listed are typical and cannot be used as accept/reject specifications

www.graftech.com | graftechcustomersupport@graftech.com

**Redefining limits**

**United States of America**  
101 N. Phillippi Pike  
Ammoore, WV 26323-0120  
Ph: +1-800-842-8805  
+1-304-624-1253

**China**  
Unit 2104 of International Capital Plaza  
1318, Sichuan Road North  
Hongkou District, Shanghai China  
Ph: +86-21-8625-8018

**Italy**  
Via Forno Allione, 2  
1-25040 Malonno, Brescia, Italy  
Ph: +39-036-463-0131

**France**  
La Lechere  
73264 Aigueblanche Cedex, France  
Ph: +33-4-79-41-45-00